










## MARQUISE COLLECTION

PASTA BLANCA / WHITE BODY

Características técnicas de la base / Technical characteristics of the wall						
Especificaciones técnicas Technical specifications		Norma Iso standard	Resultados Results		Requisitos / Requirements ISO 13006: 2012 Anexo/Annex L EN 14411: 2016 Anexo/Annex L	
	Características Dimensionales Dimensions	ISO 10545-2	Varios / Various		N≥15cm	
			Longitud / Length	Anchura / Width		
	Sobre la medida de fabricación From work size		0,00%, 0,0mm / 0,12%, 0,3mm	-0,12%, -0,1mm / 0,37%, 0,3mm	±0,5% / ±2,0mm	
	Rectitud de los lados Straightness of the sides		-0,04%, -0,1mm / 0,04%, 0,1mm	0,00%, 0,0mm / 0,00%, 0,0mm	±0,3% / ±1,5mm	
	Ortogonalidad Rectangularity		-0,16%, -0,4mm / 0,16%, 0,4mm	-0,12%, -0,1mm / 0,12%, 0,1mm	±0,5% / ±2,0mm	
	Curvatura lateral Edge curvature		-0,20%, -0,5mm / 0,00%, 0,0mm	0,00%, 0,0mm / 0,00%, 0,0mm	-0,3/+0,5 % / -1,5/+2,0mm	
	Curvatura central Centre curvature		-0,19%, -0,5mm / 0,00%, 0,0mm		-0,3/+0,5 % / -1,5/+2,0mm	
	Del alabeo From warpage		-0,04%, -0,1mm / 0,04%, 0,1mm		±0,5% / ±2,0mm	
Grosor Thickness	0,00%, 0,0mm / 1,25%, 0,1mm		±10% / ±0,5mm			
	Absorción de agua Water absorption	ISO 10545-3	E=18,0% mín 17,3%		E>10% mín 9%	
	Resistencia a la flexión Modulus of rupture	ISO 10545-4	e ≥ 7,5mm		e ≥ 7,5mm	e < 7,5mm
	Fuerza de rotura Breaking strength		860N		≥600N	≥200N
	Resistencia a la flexión Modulus of rupture		Media=21 N/mm <sup>2</sup> Mín=19 N/mm <sup>2</sup>		Media ≥ 12 N/mm <sup>2</sup>	Media ≥ 15 N/mm <sup>2</sup>
	Resistencia al choque térmico Resistance to thermal shock	ISO 10545-9	Resistente / Resistant		Valor declarado / Declared value	
	Coefficiente térmico de dilatación lineal Thermal coefficient of linear expansion	ISO 10545-8	5,9 x 10 <sup>-4</sup> °K <sup>-1</sup>		Valor declarado / Declared value	
	Resistencia al cuarteo Crazing resistance	ISO 10545-11	Resistente / Resistant		Exigido / Required	
	Resistencia química Chemical resistance	ISO 10545-13				
	Productos domésticos y aditivos piscinas Household chemicals and swimming pool salts		GA		Mín GB	
	Ácidos y bases baja concentración Low concentration of acids and alkalis		GLA		Valor declarado / Declared value	
	Resistencia al manchado Stain resistance	ISO 10545-14	5		Mín 3	
	Calidad de la superficie Surface quality	ISO 10545-2	100%		≥95%	

TORONTO  
115 Carnarvon Street  
Toronto, ON M6M 3C9  
T 416 413 9008  
F 416 413 9652

TROY  
1700 Stutz Drive, Ste 92 & 94  
Troy, MI 48084  
T 248 643 6520  
F 248 643 6523

Please note, all specifications have been supplied by the manufacturer and are subject to change.

Email: mail@cercantile.com  
Website: www.cercantile.com