

TransTower Aquaprime YW010

Product Description	A water based anticorrosive primer for Transmission Towers. Contains a zinc-free anticorrosive pigment.				
Intended Use	<ul style="list-style-type: none"> For the anticorrosive protection of electricity Transmission Towers, gantries, bridges and tank externals Use with YW020 Finish for a two coat approved water based system UK National Grid approved Designed to be moisture tolerant thus enabling application on to damp steelwork, in conditions similar to those found in early morning dew or after light showers 				
Approvals/ Certification	UK National Grid				
Finish	Matt				
Volume Solids	55 ± 2%				
VOC Content	75 ± 20 g/litre				
Film Thickness Range And Coverage		Dry Film Thickness	Wet Film Thickness	Theoretical Coverage	
	Typical	50 µm	91 µm	11.0 m ² /litre	
	Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated – see Product Notes				
Drying Times	Applied to 50 microns DFT	+10°C	+23°C	+35°C	
	Dust Free	6 hr	4 hr	2 hr	
	Hard Dry	24 hr	16 hr	8 hr	
	Overcoating	Minimum	12 hr	8 hr	6 hr
		Maximum	Indefinite if surface is clean and sound		
	Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation				
Colours	Buff				
Product Code	30STTTOW-W10				
SG	1.65 – 1.75 kg/lt				
Storage Conditions	Store in dry, cool conditions and protect from freezing – water based product				
Shelf Life	Minimum 12 months if stored as above in unopened containers				
Flash Point	Above 60°C				

TransTower Aquaprime YW010

<p>Surface Preparation</p>	<ul style="list-style-type: none"> All surfaces to be coated should be dry and cleaned as necessary to remove all oil, grease, salts or other contamination. Where necessary, remove weld spatter and grind smooth all sharp edges and weld seams Blast clean to Sa2½ (ISO 8501-1:2007), surface profile 50-75 microns Where blast cleaning is impractical, loose scale or rust should be removed by wire brush to standard St2 (ISO 8501-1:2007), taking care to avoid 'polishing' the surface For surfaces other than bare Steel, please consult Axalta Coating Systems 														
<p>Mixing</p>	<p>Must be mixed thoroughly before use. Product is designed to be highly thixotropic to allow high build application by brush.</p>														
<p>Thinner</p>	<p>DO NOT THIN Equipment Cleaner Clean water</p>														
<p>Application Conditions</p>	<p>Only apply in conditions of good ventilation which must be maintained during drying and curing. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time of the paint coating, the surface should be dry, the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point.</p>														
<p>Application Methods</p>	<table border="1" data-bbox="448 929 1495 1064"> <thead> <tr> <th data-bbox="448 929 675 1003">Method</th> <th data-bbox="675 929 922 1003">Airless Spray</th> <th data-bbox="922 929 1169 1003">Conventional Spray</th> <th data-bbox="1169 929 1339 1003">Brush</th> <th data-bbox="1339 929 1495 1003">Roller</th> </tr> </thead> <tbody> <tr> <td data-bbox="448 1003 675 1064"></td> <td data-bbox="675 1003 922 1064">Yes</td> <td data-bbox="922 1003 1169 1064">No</td> <td data-bbox="1169 1003 1339 1064">Yes</td> <td data-bbox="1339 1003 1495 1064">No</td> </tr> </tbody> </table> <ul style="list-style-type: none"> This product is designed for brush application without thinning For airless spray application, please contact Axalta Coating Systems for advice 					Method	Airless Spray	Conventional Spray	Brush	Roller		Yes	No	Yes	No
Method	Airless Spray	Conventional Spray	Brush	Roller											
	Yes	No	Yes	No											
<p>Product Notes</p>	<p>System For maximum corrosion resistance, it is recommended to apply 1 coat of YW010 to a dry film thickness of 40- 60 microns, followed by 1 coat of YW020 Finish to a dry film thickness of 100 - 150 microns (average 125µm).</p> <p>Practical Spreading Rate Due to high volume solids of this primer, which are in accordance with the 1991 National Grid specifications, and also widely varying application conditions (ambient temperatures, wind velocities, contactor application techniques, losses etc.) practical spreading rates will vary and generally fall in the range of 3 - 4 sq.m. per litre.</p>														
<p>Health & Safety</p>	<p>Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.</p>														

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.