

Floorcote Non-Skid Deck Paint

Product Description	A modified-alkyd floor coating containing an anti-slip aggregate.				
Features & Use	<ul style="list-style-type: none"> • A single pack, easily applied deck and floor coating • For metal and wooden decks on seagoing vessels and concrete floors in buildings • Rapid drying to minimise downtime 				
Approvals/ Certification	Conforms to Category (i) of Directive 2004/42/EC, which carries a VOC limit of 500g/l				
Finish	Anti-slip				
Volume Solids	51 ± 2% (varies with colour)				
VOC Content	317 ± 20 g/litre (varies with colour)				
Film Thickness Range And Coverage		Dry Film Thickness	Wet Film Thickness	Theoretical Coverage	
	Typical	90 µm	176 µm	5.6 m ² /litre	
	Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated				
Drying Times	Applied to 90 microns DFT		+10°C	+23°C	
	Dust Free		5 hr	3 hr	
	Hard Dry		7 hr	5 hr	
	Overcoating	Minimum	16 hr	16 hr	16 hr
		Maximum	See Product Notes		
Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation					
Colours	Cornflower Blue, Red Oxide, Grey, Green				
Product Code	09NSD				
SG	1.55 kg/lit (varies with colour)				
Storage Conditions	Store in dry, cool conditions and protect from frost				
Shelf Life	Minimum 12 months if stored as above in unopened containers				
Flash Point	23-60°C				

Floorcote Non-Skid Deck Paint

Surface Preparation	<ul style="list-style-type: none"> All surfaces must be clean, dry, and free from grease, oil, laitance, dust and other contamination Floorcote Non-Skid Deck Paint should be applied over suitably primed or sealed substrates. Consult Axalta Coating Systems for specification advice 				
Mixing	Mix thoroughly before use. Agitate periodically during use to ensure product remains homogeneous.				
Thinner	Not recommended Equipment Cleaner No.3 Thinner				
Application Conditions	<ul style="list-style-type: none"> Only apply in conditions of good ventilation which must be maintained during drying and curing. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time of the paint coating, the surface should be dry, the Relative Humidity should not exceed 85% and the substrate temperature should remain at least 3°C above the dew point. Only apply this product when the above conditions can be maintained throughout the critical application and drying/curing process. Paint temperature should ideally be at a minimum of 15°C. 				
Application Methods	Method	Airless Spray	Conventional Spray	Brush	Roller
		No	No	Yes	Yes
Product Notes	<ul style="list-style-type: none"> Overcoating: this product is normally applied as a single coat application. It may be overcoated after an indefinite period with suitable topcoats. Due to the anti-slip textured surface, careful cleaning will be required before overcoating to ensure removal of all contamination This product contains anti-slip aggregate to provide a rougher surface than conventional deck coatings. The risk of slipping will therefore be reduced, but not eliminated. Normal precautions against slipping accidents must still be taken 				
Health & Safety	Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.				

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.