

Stokes French Polish

Product Description	French Polish for use on wood.
Features & Use	<ul style="list-style-type: none"> • Produces the deep lustrous finish of 'Grand Piano standard' on furniture, cupboards and other decorative woodwork • Resists the action of White Spirit and similar non-alcohol solvents • Has a very high electric strength and anti-tracking properties • Consists of Shellac solution in methylated spirits
Approvals/ Certification	Please consult Axalta Coating Systems
Finish	n/a
Volume Solids	28 ± 2%
VOC Content	576 ± 20 g/litre
Product Code	20POL-011
SG	0.87 kg/lt
Storage Conditions	Store in dry, cool conditions and protect from frost
Shelf Life	Minimum 12 months if stored as above in unopened containers
Flash Point	Below 21°C – LOW FLASH MATERIAL. Observe low flash regulations
Surface Preparation	<ul style="list-style-type: none"> • Surfaces should be clean, dry and free from all grease, oil, loose material and general contamination. Sand wood smooth with very fine abrasive paper and dust off
Product Notes	<ul style="list-style-type: none"> • Dries in 15-20 minutes, overcoatable 30 minutes at 23°C • Clean with TH002 Thinner (Methylated Spirit) • French Polishes are not suitable for surfaces which are liable to be heated • Apply the first 2 coats by brush if the wood is very absorbent, then apply further coats by Pad or Swab. Apply coats of French Polish until the desired finish is obtained. This may involve as many as 20 coats if a very high gloss finish is required
Health & Safety	Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of

design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.