

Stormcote Acrylated Rubber Masonry Paint

Product Description	A highly durable Pliolite-based masonry paint.				
Features & Use	<ul style="list-style-type: none"> • Can be applied year-round in low temperatures • Shower-proof within 30 minutes • Excellent protection from algae and fungal attack and extreme weather conditions • Microporous nature and resistant to dirt pick-up • Use for exterior masonry, cement, stone, brick etc. where good alkali resistance is required 				
Approvals/ Certification	Conforms to Category 'c' of 2004/42/EC which carries a VOC limit of 430 g/litre				
Finish	Smooth matt				
Volume Solids	48 ± 2% (varies with colour)				
VOC Content	<430 g/litre (varies with colour)				
Film Thickness Range And Coverage		Dry Film Thickness	Wet Film Thickness	Theoretical Coverage	
	Typical	50 µm	104 µm	9.6 m ² /litre	
	Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated				
Drying Times	Applied to 50 microns DFT	+10°C	+23°C	+35°C	
	Dust Free	2 hr	1 hr	30 min	
	Hard Dry	4 hr	3 hr	2 hr	
	Overcoating	Minimum	18 hr	12 hr	6 hr
		Maximum	Indefinite if clean and sound		
	Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation				
Colours	White plus limited range				
Product Code	01SAR-				
SG	1.54 kg/lt (varies with colour)				
Storage Conditions	Store in dry, cool conditions and protect from frost				
Shelf Life	Minimum 12 months if stored as above in unopened containers				
Flash Point	23-60°C				

Stormcote Acrylated Rubber Masonry Paint

Surface Preparation	<ul style="list-style-type: none"> Surfaces should be clean, dry and free from all grease, oil, loose material and general contamination Unsound surfaces should be scraped back to firm edge If bacterial contamination is present, wash with a bleach solution (observing necessary safety precautions) 				
Mixing	Must be mixed thoroughly before use. Agitate periodically to ensure paint remains homogeneous.				
Thinner / Cleaner	Axalta Thinner General Industrial TH004 (formerly called No.7 Thinner)				
Application Conditions	Only apply in conditions of good ventilation which must be maintained during drying and curing. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time of the paint coating, the surface should be dry, the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point. Paint temperature should ideally be at a minimum of 15°C.				
Application Methods	Method	Airless Spray	Conventional Spray	Brush	Roller
		No	No	Yes	Yes
Product Notes	<ul style="list-style-type: none"> Apply a first coat thinned approx. 15% to act as a sealer, followed by 2 full coats Do not apply to damp or frosted surfaces This coating has not been tested to the standard of the new regulation 7(2) of the Building Regulations 2010, which came into force in Dec 2018 				
Health & Safety	Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.				

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.