



FLOWCRETE AMERICAS CHEMICAL RESISTANCE CHART

Chemical resistance tests have been completed on the full range of Flowcrete Americas' polymer flooring systems to determine the material's performance when exposed to a wide range of chemicals and solvents.

Tests have been carried out on sample systems that have been pigmented light gray in color. All test pieces were cast as 8" x 8" x 1 9/16" coupons (grouted and sealed where appropriate) and allowed to fully cure for 10 days at 70°F prior to being tested in accordance with the schedules described below.

The results detailed in the tables below should be considered as the most extreme circumstances as test pieces were completely immersed in test solutions. In practice, aggressive chemicals only come into contact with the uppermost working surface of any floor system, which significantly reduces the aggressive potential of a given chemical. Additionally, these effects should be minimized in practice by good house keeping and cleaning regimes.

In the absence of specific chemical contact data or combinations of chemicals listed below please contact our technical department or laboratories who will be pleased to advise you based upon experience from previous case histories.

Chemical Resistance Rating Guide

The following Chemical Resistance Chart is categorized by the following rating system:

Rating	Description	Explanation
5	Excellent	No harmful effect action after long-term contact.
3	Medium Term	Unaffected after 1 month contact but may begin to fail thereafter.
1	Short Term	Unaffected after 24 hours contact but may begin to fail thereafter.
0	Non Resistant	Attacked on contact or within 2-3 hours.
A	This chemical will attack silica. Non-silica aggregate and/or reinforcing fabric must be used.	
D	The coating may stain or begin to shift color when exposed to this chemical.	

- Discoloration/staining is not classified as chemical attack if hardness is unchanged.
- Higher temperatures will reduce the chemical resistance shown in the performance table.
- Some chemicals may concentrate due to evaporation and become more aggressive.
- Mixtures of chemicals can be more aggressive than might be expected from the individual components alone.
- Solvent resistant performances, in practice, are expected to exceed the values noted in the performance table due to good housekeeping combined with evaporation.
- The chemical resistance of Epoxy screed systems will be influenced by the integrity of the surface sealer – this being dependent upon service conditions and housekeeping.
- The assessment is based on a resin rich screed where permeation by liquid chemicals is minimal.
- The use of a highly filled screed will significantly reduce the chemical resistance shown in the performance table.





General Purpose Epoxy Coatings Heavy Industrial Epoxy Coatings Solvent Free Epoxy Screeds Waterborne Epoxy Coatings Polyurethane Coatings Cementitious Urethane Flexible Polyurethane Coatings Vinyl Esters

Flowcrete Americas' Flooring Systems

Flowchem VE BC								✓
Flowchem VE GL								✓
Flowchem VE RC								✓
Flowcoat CR		✓						
Flowcoat ESD	✓							
Flowcoat HTS					✓			
Flowcoat LXP HD							✓	
Flowcoat OP	✓							
Flowcoat SF41	✓							
Flowcoat SF41 HCS					✓			
Flowcoat SKN		✓						
Flowcoat WB Satin					✓			
Flowfresh CM						✓		
Flowfresh HF						✓		
Flowfresh IF						✓		
Flowfresh MF						✓		
Flowfresh RT						✓		
Flowfresh SL						✓		
Flowfresh SR						✓		
Flowfresh SRQ						✓		
Flowfresh TZ						✓		
Flowfresh Ultra Flakes					✓			
Flowseal EPW				✓				
Flowseal Ultra Flakes					✓			
Flowshield Quartz	✓							
Flowshield SL	✓							
Flowtallics	✓							
Flowtallics UV					✓			





	General Purpose Epoxy Coatings	Heavy Industrial Epoxy Coatings	Solvent Free Epoxy Screeds	Waterborne Epoxy Coatings	Polyurethane Coatings	Cementitious Urethane	Flexible Polyurethane Coatings	Vinyl Esters
Flowtex			✓					
Kristalina	✓							
Mondéco Classic			✓					
Mondéco Crystal			✓					
Mondéco Earth			✓					
Mondéco Exotic			✓					
Mondéco TZ						✓		
Peran Floor Flakes	✓							
Peran STB	✓							
Peran STB Broadcast	✓							
Flowgard WW				✓				
Flowgard WW Reinforced (Standard & Super)				✓				
Rustik Natural Stone	✓							





General Purpose Epoxy Coatings Heavy Industrial Epoxy Coatings Solvent Free Epoxy Screeds Waterborne Epoxy Coatings Polyurethane Coatings Cementitious Urethane Flexible Polyurethane Coatings Vinyl Esters

A

Acetaldehyde		0	0	0	0	0	3	0	3
Acetic Acid at 70°F (21°C)	5%	0	0	0	0	1	5	0	5
Acetic Acid at 70°F (21°C)	10%	0	3	0	0	1	5	0	5
Acetic Acid at 110°F (60°C)	10%	0	0	0	0	0	0	0	5
Acetic Acid at 70°F (21°C)	20%	0	2	0	0	0	5	0	5
Acetic Acid at 70°F (21°C)	30%	0	1	0	0	0	4	0	5
Acetic Acid at 110°F (60°C)	30%	0	0	0	0	0	0	0	5
Acetic Anhydride		0	2	0	0	0	5	0	5
Acetone		0	0	0	0	0	0	0	3
Acetonitrile		0	0	0	0	0	5	0	3
Acetyl Chloride		0	2	0	0	3	5	3	5
Acrolein		0	1	0	0	0	5	0	5
Acrylic Acid at 70°F (21°C)		0	2	0	0	0	5	0	5
Acrylic Methyl Ester		0	2	0	0	3	5	3	3
Acrylonitrile		0	1	0	0	0	3	0	0
Adiponitrile		3	4	3	0	3	5	3	3
Allyl Alcohol		0	3	0	0	3	5	3	3
Allyl Chloride		0	3	0	0	3	5	3	5
Aluminium Sulphate at 70°F (21°C)	30%	5	5	5	5	5	5	5	5
Amines		0	3	0	0	3	3	3	5
Ammonia 0.880 at 70°F (21°C)		0	0	0	0	0	5	0	5
Ammonia (aq. Sol'n) at 70°F (21°C)	40%	3	3	1	0	3	3	3	5
Ammonium chloride at 70°F (21°C)	30%	5	5	5	5	5	5	5	5
Ammonium Nitrate at 70°F (21°C)	30%	5	5	5	5	5	5	5	5
Amyl Acetate (Mixed Isomers)		3	3	3	3	3	5	3	5
Aniline		0	0	0	0	0	3	0	3
Aromasol H		5	5	5	3	5	5	5	5





General Purpose Epoxy Coatings Heavy Industrial Epoxy Coatings Solvent Free Epoxy Screeds Waterborne Epoxy Coatings Polyurethane Coatings Cementitious Urethane Flexible Polyurethane Coatings Vinyl Esters

B

Beer		5	5	5	5	5	5	5	5
Benzene		0	4	0	0	5	5	5	5
Benzyl Alcohol		0	0	0	0	0	5	0	5
Benzyl Chloride		0	0	0	0	0	5	0	5
Blood		5	5	5	5	5	5	5	5
Boric Acid at 70°F (21°C)	20%	3	3	3	0	3	5	3	5
Brine	30%	5	5	5	5	5	5	5	5
Butanol		3	2	3	1	1	5	1	5
Butyl Acetate		3	3	3	1	3	5	3	5
Butyl Acrylate		5	3	5	3	3	5	3	5
Butyl Benzyl Phthalate		5	3	5	3	3	5	3	5
Butyl Ether		5	5	5	5	5	5	5	5
Butyric Acid		0	1	0	0	0	3	0	5
Butyrolactone		0	1	0	0	0	3	0	3

C

Calcium Carbonate Sol'n	Sat'd	5	5	5	5	5	5	5	5
Calcium Hydroxide susp'n	30%	5	5	5	5	5	5	5	5
Caprolactam at 70°F (21°C)	20%	3	5	3	3	5	5	5	5
Caprolactam at 70°F (21°C)	30%	3	5	3	3	5	5	5	5
Caprolactam at 70°F (21°C)	50%	3	5	3	3	5	5	5	5
Caprolactam at 70°F (21°C)	100%	3	5	3	3	5	5	5	5
Carbon Tetrachloride		3	5	3	3	5	5	5	5
Castor Oil		5	5	5	5	5	5	5	5
Chicken Fats		3	3	5	0	3	5	3	5
Chloride of Lime Sol'n at 70°F (21°C)	1%	5		5	3	5	5	5	5
Chlorinated Paraffin		5	3	5	3	3	5	3	5
Chlorobenzene		0	0	0	0	0	3	0	5
Chloroform		0	0	0	0	0	0	0	0





		General Purpose Epoxy Coatings	Heavy Industrial Epoxy Coatings	Solvent Free Epoxy Screeds	Waterborne Epoxy Coatings	Polyurethane Coatings	Cementitious Urethane	Flexible Polyurethane Coatings	Vinyl Esters
Chromic Acid at 70°F (21°C)	1%	5	5	3	1	5	5	5	5
Chromic Acid at 70°F (21°C)	5%	3	1	3	0	3	3	1	5
Chromic Acid at 70°F (21°C)	10%	3	1	3	0	3	3	1	5
Chromic Acid at 70°F (21°C)	30%	1	1	1	0	3	3	1	1
Ciopen A30		5	5	5	3	5	5	5	5
Ciopen A60		5	5	5	3	5	5	5	5
Citric Acid at 70°F (21°C)	10%	5	5	5	3	5	5	5	5
Citric Acid at 70°F (21°C)	30%	5	5	5	3	5	5	5	5
Cleaning agent for heavy duty vehicles	10%	3	0	3	0	0	5	0	5
Cleaning agent for heavy duty vehicles – concentrate		3	0	3	0	0	5	0	5
Cleaning Petrol		5	5	5	5	5	5	5	5
Coconut Fatty Acid		5	5	5	5	5	5	5	5
Coconut Oil		5	5	5	5	5	5	5	5
Cod Liver Oil		5	5	5	5	5	5	5	5
Common Salt Sol'n at 70°F (21°C)	5%	5	5	5	5	5	5	5	5
Common Salt Sol'n	Sat'd	5	5	5	5	5	5	5	5
Copper Sulphate Sol'n at 70°F (21°C)	30%	5	5	5	5	5	5	5	5
Cotton Seed Oil		5	5	5	5	5	5	5	5
Creosote		5	3	5	3	3	5	3	3
Cresylic Acid		0	0	0	0	0	3	0	3
Crotonaldehyde		0	0	0	0	0	3	0	5
Crude Oil		5	5	5	5	5	5	5	5
Cyclohexane		5	5	5	5	5	5	5	5
Cyclohexanol		5	5	5	3	5	5	5	5
Cyclohexanone		0	4	0	0	5	5	5	5
D									
Decanol		5	5	5	5	5	5	5	5
Deionized Water		5	5	5	5	5	5	5	5





		General Purpose Epoxy Coatings	Heavy Industrial Epoxy Coatings	Solvent Free Epoxy Screeds	Waterborne Epoxy Coatings	Polyurethane Coatings	Cementitious Urethane	Flexible Polyurethane Coatings	Vinyl Esters
Detergent Solution	3%	5	5	5	5	5	5	5	5
Diacetone Alcohol		5	5	5	3	5	5	5	3
Dibutyl Phthalate		5	5	5	5	5	5	5	5
Dichlorobenzene		5	3	5	3	3	5	3	5
Dichloroethane		0	0	0	0	0	3	0	3
Dichloroethylene		0	1	0	0	0	5	0	3
Dichloromethane		0	0	0	0	0	5	0	0
Dichloropropane		5	5	5	0	5	5	5	3
Dicyclopentadiene		3	4	3	3	3	5	3	5
Diesel Oil		5	5	5	5	5	5	5	5
Diethanolamine		3	3	3	3	3	5	3	5
Diethylamine (aq. Sol'n) at 70°F (21°C)	50%	0	0	0	0	0	3	0	3
Diethylamine (aq. Sol'n) at 70°F (21°C)	60%	0	0	0	0	0	0	0	3
Diethylene Glycol		0	0	0	0	0	3	0	5
Diethylene Glycol Monobutyl Ether		3	3	3	0	0	3	0	3
Diethylene Glycol Monoethyl Ether		0	1	0	0	0	3	0	3
Diethylene Glycol Monomethyl Ether		0	0	0	0	0	3	0	3
Diethylene Triamine at 70°F (21°C)	100%	0	3	0	0	0	4	4	5
Diethylether		3	3	3	0	0	3	0	0
Di-isobutyl Ketone		5	5	5	3	3	5	3	5
Dimethylamine (aq.Sol'n) at 70°F (21°C)	40%	3	3	3	0	0	3	0	3
Dimethylamine (aq. Sol'n) at 70°F (21°C)	50%	0	0	0	0	0	0	0	3
2-Diethylaminoethanol		3	3	3	1	3	3	3	3
Dimethyl Formamide (DMF)		0	0	0	0	0	0	0	0
Di-N-butyl Phthalate		5	5	5	5	5	5	5	5
Di-octyl Phthalate		5	5	5	5	5	5	5	5
Dioxane		0	3	0	0	3	5	3	5





General Purpose Epoxy Coatings Heavy Industrial Epoxy Coatings Solvent Free Epoxy Screeds Waterborne Epoxy Coatings Polyurethane Coatings Cementitious Urethane Flexible Polyurethane Coatings Vinyl Esters

Dipentene		5	5	5	3	5	5	5	5
Di-Propylene Glycol		5	5	5	5	5	5	5	5
Dishwashing Detergent	3%	5	5	5	5	5	5	5	5
Dutrex 217 UK		5	5	5	0	0	5	0	5

E

Electrocoating		5	5	5	0	5	5	5	5
Epichlorohydrin		0	3	0	0	3	5	3	1
Ethanol at 70°F (21°C)	10%	5	5	5	5	5	5	5	5
Ethanol at 70°F (21°C)	15%	5	5	5	5	5	5	5	5
Ethanol at 70°F (21°C)	70%	5	5	5	3	5	5	5	5
Ethanol at 70°F (21°C)	96%	3	4	3	0	5	5	3	5
Ethanolamine		0	3	0	0	3	3	3	3
Ethyl Acetate		0	3	0	0	5	5	5	5
Ethyl Acrylate		0	3	0	0	5	5	5	5
Ethyl Benzene		3	3	3	0	3	3	3	5
Ethylene Diamine		0	3	0	0	3	3	3	3
Ethyl Glycol		5	3	5	0	3	5	3	5
Ethylene Glycol		5	5	5	5	5	5	5	5
Ethyl Glycol Acetate		5	5	5	3	5	5	5	5
Ethylene Glycol Monobutyl Ether		3	3	3	3	3	5	3	5
Ethylene Glycol Monobutyl Ether Acetate		5	5	5	3	3	5	3	3
Ethylene Glycol Monoethyl Ether		0	0	0	0	0	3	0	3
Ethylene Glycol Monoethyl Ether Acetate		3	3	3	3	3	5	3	3
Ethylene Glycol Monomethyl Ether		0	0	0	0	0	0	0	1
2-Ethyl Hexanol		5	5	5	3	3	5	3	3
2-Ethyl Hexyl Acrylate		5	5	5	3	3	5	3	3
Ethylene Amine		0	1	0	0	0	3	0	3





General Purpose Epoxy Coatings Heavy Industrial Epoxy Coatings Solvent Free Epoxy Screeds Waterborne Epoxy Coatings Polyurethane Coatings Cementitious Urethane Flexible Polyurethane Coatings Vinyl Esters

F

Fish Oil		5	5	5	5	5	5	5	5
Formaldehyde at 70°F (21°C)	40%	5	5	5	0	0	5	0	5
Formaldehyde at 70°F (21°C)	100%	3	3	3	0	0	5	0	5
Formic Acid at 70°F (21°C)	5%	3	3	3	0	0	5	0	5
Formic Acid at 70°F (21°C)	10%	3	3	3	0	0	5	0	5
Formic Acid at 70°F (21°C)	20%	0	0	0	0	0	5	0	5
Formic Acid at 70°F (21°C)	30%	0	0	0	0	0	5	0	5
Formic Acid at 70°F (21°C)	98%	0	0	0	0	0	3	0	5
Furfural		0	0	0	0	0	3	0	0
Furfuryl Alcohol		0	0	0	0	0	3	0	3

G

Glycerol		5	5	5	5	5	5	5	5
Grape Juice		3	3	3	3	3	5	3	5
Groundnut Oil		5	5	5	3	5	5	5	5

H

Heptane		5	5	5	3	5	5	5	5
Hexane		5	5	5	3	5	5	5	5
Hexylene Glycol		5	5	5	3	3	5	3	5
Hydrazine Hydrate		3	0	3	1	0	3	0	0
Hydrochloric Acid at 70°F (21°C)	5%	5	5	5	3	0	5	0	5
Hydrochloric Acid at 70°F (21°C)	10%	3	3	3	0	0	5	0	5
Hydrochloric Acid at 70°F (21°C)	36%	0	1	0	0	0	3	0	5
Hydrofluoric Acid at 70°F (21°C)	20%	0	0	0	0	0	0	0	5,A
Hydrogen Peroxide at 70°F (21°C)	3%	5	5	5	3	5	5	5	5
Hydrogen Peroxide at 70°F (21°C)	30%	3	4	3	1	5	5	5	5
Hydrogen Sulphide		3	4	3	0	3	5	3	5





General Purpose Epoxy Coatings Heavy Industrial Epoxy Coatings Solvent Free Epoxy Screeds Waterborne Epoxy Coatings Polyurethane Coatings Cementitious Urethane Flexible Polyurethane Coatings Vinyl Esters

I

Iso-Amyl Acetate		5	5	5	3	5	5	5	5
Iso-Amyl Alcohol		3	4	3	1	5	5	5	5
Iso-Butanol		3	4	3	1	5	5	5	5
Iso-Butyl Acetate		5	5	5	3	5	5	5	5
Iso-Butyl Aldehyde		0	3	0	0	3	3	3	5
Iso-Octanol		5	5	5	3	5	5	5	5
Iso-Pentane		5	5	5	3	5	5	5	5
Iso-Phorone		3	3	3	0	3	3	3	5
Iso-Phorone Diamine at 70°F (21°C)		0	2	0	0	3	3	3	3
Isoprene		3	3	3	1	3	5	3	5
Iso-Propanol		3	4	3	0	5	5	5	5

J

Jet Fuel		5	5	5	3	5	5	5	5
----------	--	---	---	---	---	---	---	---	---

K

Kerosene		5	5	5	3	5	5	5	5
----------	--	---	---	---	---	---	---	---	---

L

Lactic Acid at 70°F (21°C)	2%	5	5	5	3	5	5	5	5
Lactic Acid at 70°F (21°C)	5%	5	5	5	1	5	5	5	5
Lactic Acid at 70°F (21°C)	30%	3	3	3	0	3	5	3	5
Lactic Acid at 70°F (21°C)	90%	0	0	0	0	0	5	0	5
Lard		5	5	5	5	5	5	5	5
Lime Juice		3	3	3	0	3	5	3	5
Linseed Fatty Acid		5	5	5	5	5	5	5	5
Linseed Oil		5	5	5	5	5	5	5	5

M

Maleic Acid at 70°F (21°C)	30%	5	5	5	3	5	5	5	5
Methanol		0	4	0	0	5	5	5	5





		General Purpose Epoxy Coatings	Heavy Industrial Epoxy Coatings	Solvent Free Epoxy Screeds	Waterborne Epoxy Coatings	Polyurethane Coatings	Cementitious Urethane	Flexible Polyurethane Coatings	Vinyl Esters
Methyl Acetate		0	0	0	0	0	5	0	3
Methyl Acrylate		0	4	0	0	5	5	5	5
Methylene Chloride		0	0	0	0	0	0	0	0
Meta Cresol		0	0	0	0	0	3	0	3
Methyl Ethyl Ketone (MEK)		0	0	0	0	0	0	0	5
Methyl Glycol Acetate		3	3	3	1	3	3	3	3
Methyl Isobutyl Ketone (MIBK)		3	3	3	0	3	3	3	5
Methyl Methacrylate		0	3	0	0	3	5	3	3
N-Methyl Pyrrolidone		0	0	0	0	0	0	0	1
Milk		5	5	5	5	5	5	5	5
Mineral Oil		5	5	5	5	5	5	5	5
Molasses		5	5	5	5	5	5	5	5
Morpholine		0	0	0	0	0	3	0	1
N									
N-Amino Ethyl Piperazine at 70°F (21°C)		0	3	0	0	3	3	3	3
Naphtha (Petroleum)		5	5	5	3	3	5	3	5
Naphtha (Solvent)		5	5	5	3	3	5	3	5
Naphthenic Acid		5	5	5	5	5	5	5	5
N-Butanol		5	5	5	1	3	5	3	5
N-Butyl Acetate		5	5	5	1	3	5	3	5
N-Heptanol		5	5	5	3	5	5	5	5
N-Hexanol		5	5	5	3	5	5	5	5
Nitric Acid at 70°F (21°C)	1%	5	5	5	3	5	5	5	5,D
Nitric Acid at 70°F (21°C)	3%	5	5	5	0	5	5	5	5,D
Nitric Acid at 70°F (21°C)	5%	3	5	3	0	5	5	5	5,D
Nitric Acid at 70°F (21°C)	10%	3	5	3	0	5	5	5	5,D
Nitric Acid at 70°F (21°C)	30%	0	1	0	0	0	5	0	5,D
Nitric Acid at 70°F (21°C)	69%	0	0	0	0	0	0	0	5,D
Nitrobenzene		0	0	0	0	0	0	0	5





General Purpose Epoxy Coatings Heavy Industrial Epoxy Coatings Solvent Free Epoxy Screeds Waterborne Epoxy Coatings Polyurethane Coatings Cementitious Urethane Flexible Polyurethane Coatings Vinyl Esters

Nitro-Ethane		0	0	0	0	0	0	0	3
Nitro-Propane (Mixed Isomers)		0	0	0	0	0	3	0	5
Nonanol		5	5	5	3	3	5	3	5
Nonyl Phenol		5	5	5	3	5	5	5	5
N-Pentane		5	5	5	3	5	5	5	5

O

Octanol		5	5	5	3	5	5	5	5
Oleic Acid at 70°F (21°C)	100%	3	4	3	0	5	5	5	5
Olive Oil		5	5	5	5	5	5	5	5
Ortho Cresol		0	0	0	0	0	3	0	5
Orthophosphoric Acid at 70°F (21°C)	85%	0	3	0	0	3	5	3	5
Oxalic Acid at 70°F (21°C)	2%	5	5	5	3	3	5	3	5
Oxalic Acid at 70°F (21°C)	10%	3	4	3	0	5	5	5	5

P

Palm Kernel Oil		5	5	5	5	5	5	5	5
Para Cresol (aq)		0	0	0	0	0	3	0	5
Paraffin		5	5	5	5	5	5	5	5
Paraffin Wax		5	5	5	5	5	5	5	5
Pentane (Mixed Isomers)		5	5	5	3	5	5	5	5
Perchlorethylene		3	5	3	1	5	5	5	5
Perchloric Acid at 70°F (21°C)	30%	3	3	3	0	3	4	3	5
Petrol		5	5	5	5	5	5	5	5
Petroleum Ether		5	5	5	3	5	5	5	5
Phenol		0	0	0	0	0	0	0	1
Phosphoric Acid at 70°F (21°C)	5%	5	5	5	0	5	5	5	5
Phosphoric Acid at 70°F (21°C)	10%	5	5	5	0	5	5	5	5
Phosphoric Acid at 70°F (21°C)	20%	5	5	5	0	5	5	5	5
Phosphoric Acid at 70°F (21°C)	50%	5	5	5	0	5	5	5	5
Photographic Developer Sol'n	10%	5	5	5	5	5	5	5	5





General Purpose Epoxy Coatings Heavy Industrial Epoxy Coatings Solvent Free Epoxy Screeds Waterborne Epoxy Coatings Polyurethane Coatings Cementitious Urethane Flexible Polyurethane Coatings Vinyl Esters

Pine Oil		5	5	5	5	5	5	5	5
Polypropylene Glycol		5	5	5	5	5	5	5	5
Potassium Dichromate at 70°F (21°C)	20%	5	5	5	3	3	5	3	5
Potassium Hydroxide Sol'n at 70°F (21°C)	5%	5	5	5	5	5	5	5	5
Potassium Hydroxide Sol'n at 70°F (21°C)	10%	5	5	5	5	5	5	5	5
Potassium Hydroxide Sol'n at 212°F (100°C)	10%	5	5	5	5	5	5	5	5
Potassium Hydroxide Sol'n at 212°F (100°C)	20%	5	5	5	5	5	5	5	5
Potassium Hydroxide Sol'n at 70°F (21°C)	50%	5	5	5	5	5	5	5	5
Pyridine		0	3	0	0	3	3	3	0
Pyridine Bases		0	3	0	0	3	3	3	0

S

Seawater		5	5	5	5	5	5	5	5
Sec-Butanol		5	3	5	3	3	5	3	5
Shell Rotella Oil		5	5	5	5	5	5	5	5
Shellsol A		5	5	5	3	3	5	3	5
Shellsol T		5	5	5	3	3	5	3	5
Silicone Oil		5	5	5	5	5	5	5	5
Skydrol A500		5	5	5	0	5	5	5	5
Soap Solution		5	5	5	5	5	5	5	5
Soda Solution (Saturated)		5	5	5	5	5	5	5	5
Soda Solution (Dilute)		5	5	5	5	5	5	5	5
Sodium Chloride (Sat'd Sol'n)		5	5	5	5	5	5	5	5
Sodium Dichromate Aq. Sol'n at 70°F (21°C)	33%	5	5	5	3	3	5	3	5
Sodium Bicarbonate (Aq)		5	5	5	5	5	5	5	5
Sodium Hydroxide at 70°F (21°C)	5%	5	5	5	5	5	5	5	5
Sodium Hydroxide at 70°F (21°C)	20%	5	5	5	5	5	5	5	5





General Purpose Epoxy Coatings Heavy Industrial Epoxy Coatings Solvent Free Epoxy Screeds Waterborne Epoxy Coatings Polyurethane Coatings Cementitious Urethane Flexible Polyurethane Coatings Vinyl Esters

Sodium Hydroxide at 70°F (21°C)	50%	5	5	5	5	5	5	5	5
Sodium Hydroxide at 110°F (60°C)	50%	0	0	0	0	0	0	0	5
Sodium Hypochlorite Sol'n 15% Available Cl at 70°F (21°C)		5	5	5	1	5	5	3	3,A
Sodium Nitrate at 70°F (21°C)	20%	5	5	5	5	5	5	5	5
Solvesso 150		5	3	5	3	3	5	3	5
Soya Bean Oil		5	5	5	5	5	5	5	5
Stannic Chloride		5	5	5	3	5	5	5	5
Styrene		3	3	3	0	3	5	3	5
Succinic Acid	10%	5	5	5	0	0	5	0	5
Sugar Solution at 70°F (21°C)	30%	5	5	5	5	5	5	5	5
Sulphuric Acid at 70°F (21°C)	5%	5	5	5	0	3	5	3	5
Sulphuric Acid at 70°F (21°C)	10%	5	5	5	0	3	5	3	5
Sulphuric Acid at 212°F (100°C)	10%	0	0	0	0	0	0	0	5
Sulphuric Acid at 70°F (21°C)	20%	5	5	5	0	0	5	0	5
Sulphuric Acid at 70°F (21°C)	30%	3	3	3	0	0	3	0	5
Sulphuric Acid at 70°F (21°C)	50%	3	3	3	0	0	3	0	5
Sulphuric Acid at 70°F (21°C)	98%	0	0	0	0	0	0	0	0
Sunflower Seed Oil		5	5	5	5	5	5	5	5

T

Tall Oil		5	5	5	5	5	5	5	5
Tall Oil Fatty Acid		5	5	5	5	5	5	5	5
Tallow		5	5	5	5	5	5	5	5
Tapwater		5	5	5	5	5	5	5	5
Tartaric Acid at 70°F (21°C)	5%	5	5	5	0	5	5	5	5
Tartar Solution at 70°F (21°C)	5%	5	5	5	0	0	5	0	5
Teepol		5	5	5	3	5	5	5	5
Tert-Butanol		5	5	5	3	3	5	3	5
Tetrachloroethylene		5	5	5	0	3	5	3	5



General Purpose Epoxy Coatings Heavy Industrial Epoxy Coatings Solvent Free Epoxy Screeds Waterborne Epoxy Coatings Polyurethane Coatings Cementitious Urethane Flexible Polyurethane Coatings Vinyl Esters

Tetrahydrofuran (Thf)		0	0	0	0	0	3	0	0
Tetrahydronaphthalene		5	5	5	0	3	5	3	5
Titanium Tetrachloride		3	3	3	0	3	3	3	5
Toluene		0	0	0	0	1	1	0	5
Toluene-Di-Isocyanate		5	5	5	3	5	5	5	5
Tributyl Citrate		5	5	5	3	5	5	5	5
1,1,1 – Trichloroethane		5	5	5	0	0	5	0	5
Trichloroethylene		0	0	0	0	0	0	0	5
Tri Cresyl Phosphate		5	5	5	5	5	5	5	5
Triethanolamine		5	5	5	0	3	5	3	5
Triethylene Glycol		5	5	5	3	5	5	5	5
Triethylene Cetramine		0	3	0	0	3	5	3	5
Triolyl Phosphate		5	5	5	5	5	5	5	5
Trixylyl Phosphate		5	5	5	5	5	5	5	5

U

Urea at 70°F (21°C)	30%	5	5	5	5	5	5	5	5
---------------------	-----	---	---	---	---	---	---	---	---

V

Vegetable Juice		5	5	5	5	5	5	5	5
-----------------	--	---	---	---	---	---	---	---	---

W

Water at 70°F (21°C)		5	5	5	5	5	5	5	5
Water, Distilled at 212°F (100°C)		5	5	5	5	5	5	5	5
Whisky		3	5	3	1	5	5	5	5
White Spirit		5	5	5	5	5	5	5	5
Wine		3	5	3	1	5	5	5	5

X

Xylene (mixed Isomers)		3	3	3	1	5	5	1	5
------------------------	--	---	---	---	---	---	---	---	---

